

BG58

绿色胶带基膜

Green tape base film



本产品为内添加型绿色、双面或单面电晕处理的聚酯薄膜。适用于制作锂电池终止胶带。

产品特性

- 绿色，潘通色 2255C~2258C
- 膜面平整，加工性能好
- 热稳定性好
- 耐受电解液，颜色在电解液中不析出

产品应用

- 锂电池终止胶带
- 其他电子胶带

产品性能

测试项目		单位	典型值				测试方法
厚度		μm	6	8	12	25	GB/T 6672
透光率		%	50	50	50	50	GB/T 2410
雾度		%	53	53	53	53	GB/T 2410
拉伸强度	MD	Mpa	170	190	210	250	GB/T 1040.3
	TD	Mpa	155	170	190	230	GB/T 1040.3
断裂伸长率	MD	%	95	95	100	130	GB/T 1040.3
	TD	%	90	90	90	155	GB/T 1040.3
热收缩率 150°C@30min	MD	%	1.55	1.55	1.55	1.20	GB/T 1040.3
	TD	%	0.01	0.01	0.01	0.01	GB/T 1040.3
湿润张力		达因	48	48	50	52	GB/T 14216
溶剂浸泡		无颜色析出；溶液冷却后无悬浮、无浑浊				85°C*48h	

1、以上测试结果是基于我们对该测试方法的理解，并结合我们的测试设备的实际情况和测试条件，得出的典型值，不能理解为产品的保证值。The above test results are based on our understanding of the testing method, combined with the actual conditions of our testing equipment, and represent typical values; they should not be interpreted as guaranteed values for the product

2、MD：纵向；TD：横向。MD: Machine Direction; TD: Transverse Direction

3、使用前请参见 MSDS 表 (Material Safety Data Sheet)。 Please refer to the MSDS (Material Safety Data Sheet) before use.

BG58

绿色胶带基膜

Green tape base film



This product is internally tinted green polyester film with single-sided or double-sided corona treatment, designed for manufacturing lithium battery termination tape.

Features

- Green, Pantone 2255C~2258C
- Excellent surface flatness and good processability
- Good thermal stability
- Resistant to electrolyte; no color bleeding in electrolyte

Application

- Lithium battery termination tape
- Other electronic adhesive tapes

Performance

Items		Unit	Typical Value				Test Method
Thickness		μm	6	8	12	25	GB/T 6672
Light Transmittance		%	50	50	50	50	GB/T 2410
Haze		%	53	53	53	53	GB/T 2410
Tensile strength	MD	Mpa	170	190	210	250	GB/T 1040.3
	TD	Mpa	155	170	190	230	GB/T 1040.3
Elongation at break	MD	%	95	95	100	130	GB/T 1040.3
	TD	%	90	90	90	155	GB/T 1040.3
Thermal shrinkage 150°C@30min	MD	%	1.55	1.55	1.55	1.20	GB/T 1040.3
	TD	%	0.01	0.01	0.01	0.01	GB/T 1040.3
Wetting Tension		mN/m	48	48	50	52	GBT14216
Solvent immersion			No color bleeding; no suspension or turbidity after the solution cools down				85°C*48h

1、以上测试结果是基于我们对该测试方法的理解，并结合我们的测试设备的实际情况和测试条件，得出的典型值，不能理解为产品的保证值。The above test results are based on our understanding of the testing method, combined with the actual conditions of our testing equipment, and represent typical values; they should not be interpreted as guaranteed values for the product

2、MD：纵向；TD：横向。MD: Machine Direction; TD: Transverse Direction

3、使用前请参见 MSDS 表 (Material Safety Data Sheet)。 Please refer to the MSDS (Material Safety Data Sheet) before use.