

BHS50

透明超高收缩膜

Transparent Hige-shrinkage Film



本产品为透明的聚酯薄膜。通过特殊的在线处理工艺，具有更高的收缩率和优异的平整性，可在绝缘收缩套管、收缩包装等使用场景中，提供紧密均匀的包裹。

产品特性

- 透明
- 膜面平整优异，加工性能好
- 更高的收缩率，能提供紧密均匀的包裹。

产品应用

- 绝缘套管
- 收缩包装

产品性能

测试项目		单位	典型值				测试方法
厚度		μm	15	25	50	75	GB/T 6672
透光率		%	88	88	87	87	GB/T 2410
雾度		%	2.0	2.0	3.0	3.0	GB/T 2410
拉伸强度	MD	Mpa	270	265	240	240	GB/T 1040.3
	TD	Mpa	270	270	250	245	GB/T 1040.3
断裂伸长率	MD	%	115	120	135	145	GB/T 1040.3
	TD	%	90	95	105	110	GB/T 1040.3
热收缩率 150℃@30min	MD	%	55.0	55.0	55.0	55.0	GB/T 1040.3
	TD	%	50.0	50.0	50.0	50.0	GB/T 1040.3

1、以上测试结果是基于我们对该测试方法的理解，并结合我们的测试设备的实际情况和测试条件，得出的典型值，不能理解为产品的保证值。The above test results are based on our understanding of the testing method, combined with the actual conditions of our testing equipment, and represent typical values; they should not be interpreted as guaranteed values for the product

2、MD：纵向；TD：横向。MD: Machine Direction; TD: Transverse Direction

3、使用前请参见 MSDS 表 (Material Safety Data Sheet)。 Please refer to the MSDS (Material Safety Data Sheet) before use.

BHS50



透明超高收缩膜

Transparent Hige-shrinkage Film

This product is a transparent polyester film. With a special in-line treatment process, it achieves an elevated shrink rate and excellent flatness, enabling tight and uniform wrapping for applications including insulating shrink sleeves and shrink-wrap packaging.

Features

- Transparent
- Excellent film-surface flatness and favorable processability
- Higher shrinkage rate ensures tight and uniform wrapping.

Application

- Insulating sleeves
- Shrink-wrap packaging

Performance

Items		Unit	Typical Value				Test Method
Thickness		μm	15	25	50	75	GB/T 6672
Light Transmittance		%	88	88	87	87	GB/T 2410
Haze		%	2.0	2.0	3.0	3.0	GB/T 2410
Tensile strength	MD	Mpa	270	265	240	240	GB/T 1040.3
	TD	Mpa	270	270	250	245	GB/T 1040.3
Elongation at break	MD	%	115	120	135	145	GB/T 1040.3
	TD	%	90	95	105	110	GB/T 1040.3
Thermal shrinkage 150°C@30min	MD	%	55.0	55.0	55.0	55.0	GB/T 1040.3
	TD	%	50.0	50.0	50.0	50.0	GB/T 1040.3

1、以上测试结果是基于我们对该测试方法的理解，并结合我们的测试设备的实际情况和测试条件，得出的典型值，不能理解为产品的保证值。The above test results are based on our understanding of the testing method, combined with the actual conditions of our testing equipment, and represent typical values; they should not be interpreted as guaranteed values for the product

2、MD：纵向；TD：横向。MD: Machine Direction; TD: Transverse Direction

3、使用前请参见 MSDS 表 (Material Safety Data Sheet)。 Please refer to the MSDS (Material Safety Data Sheet) before use.