

ZQH210

高强度基膜

High Tensile Strength Base Film

本产品为透明聚酯薄膜。产品纵横向拉伸强度高，特别适合于制备高拉力工况下的胶带或标签。

产品特性

- 透明
- 拉伸强度高，机械性能好
- 优异的加工性能

产品应用

- 高强度胶带
- 特种标签

产品性能

测试项目		单位	典型值				测试方法
厚度		μm	20	25	30	36	GB/T 6672
透光率		%	87.0	87.0	87.0	87.0	GB/T 2410
雾度		%	5.0	5.0	6.0	6.0	GB/T 2410
拉伸强度	MD	Mpa	320	330	330	330	GB/T 1040.3
	TD	Mpa	290	290	290	290	GB/T 1040.3
断裂伸长率	MD	%	110	110	110	110	GB/T 1040.3
	TD	%	130	130	140	140	GB/T 1040.3
热收缩率 150°C@30min	MD	%	4.5	5.0	5.0	6.0	GB/T 1040.3
	TD	%	0.2	0.1	0.1	0.1	GB/T 1040.3

1、以上测试结果是基于我们对该测试方法的理解，并结合我们的测试设备的实际情况和测试条件，得出的典型值，不能理解为产品的保证值。The above test results are based on our understanding of the testing method, combined with the actual conditions of our testing equipment, and represent typical values; they should not be interpreted as guaranteed values for the product

2、MD：纵向；TD：横向。MD: Machine Direction; TD: Transverse Direction

3、使用前请参见 MSDS 表 (Material Safety Data Sheet)。 Please refer to the MSDS (Material Safety Data Sheet) before use.

ZQH210

高强度基膜

High Tensile Strength Base Film

This product is a transparent polyester film with high tensile strength in both machine and transverse directions, making it especially suitable for manufacturing tapes or labels subjected to high-tension working conditions.

Features

- Transparent
- High tensile strength and excellent mechanical properties
- Outstanding processability

Application

- High-strength adhesive tapes
- Special labels

Performance

Items		Unit	Typical Value				Test Method
Thickness		μm	20	25	30	36	GB/T 6672
Light Transmittance		%	87.0	87.0	87.0	87.0	GB/T 2410
Haze		%	5.0	5.0	6.0	6.0	GB/T 2410
Tensile strength	MD	Mpa	320	330	330	330	GB/T 1040.3
	TD	Mpa	290	290	290	290	GB/T 1040.3
Elongation at break	MD	%	110	110	110	110	GB/T 1040.3
	TD	%	130	130	140	140	GB/T 1040.3
Thermal shrinkage 150°C@30min	MD	%	4.5	5.0	5.0	6.0	GB/T 1040.3
	TD	%	0.2	0.1	0.1	0.1	GB/T 1040.3

1、以上测试结果是基于我们对该测试方法的理解，并结合我们的测试设备的实际情况和测试条件，得出的典型值，不能理解为产品的保证值。The above test results are based on our understanding of the testing method, combined with the actual conditions of our testing equipment, and represent typical values; they should not be interpreted as guaranteed values for the product

2、MD：纵向；TD：横向。MD: Machine Direction; TD: Transverse Direction

3、使用前请参见 MSDS 表 (Material Safety Data Sheet)。 Please refer to the MSDS (Material Safety Data Sheet) before use.